

## Product Information

06.09.2023

## MARLOSOL ST 9150 P

### Composition

Polyoxypropylenstearyl ether  
 INCI US: PPG-15 Stearyl Ether  
 INCI EU: PPG-15 Stearyl Ether

Distribuito da:



**Tellerini s.p.a.**

Via Bonazzi, 36  
 40013 Castel Maggiore (BO)  
 Tel: +39 051 6322111  
 Fax: +39 051 715380  
[sicurezza@tellerini.it](mailto:sicurezza@tellerini.it)  
[www.tellerini.it](http://www.tellerini.it)

### Product data (specification)

Property	Value	Unit	Test method
Appearance at 20 °C	clear, liquid	-	visuell
Acid number	max. 1.0	mg KOH/g	DIN EN ISO 2114
Hydroxyl number	62 - 77	mg KOH/g	DIN EN 13926
Water content	max. 0.7	% by mass	DIN EN 13267
Colour (APHA)	≤ 50	mg Pt/l	DIN EN 1557
Iodine number	≤ 5	g I <sub>2</sub> /100g	DIN EN ISO 3961
Peroxid content	≤ 5	meq O <sub>2</sub> /kg	DGF C-VI 6A
BHT content	0.03 - 0.1	% by mass	HPLC
pH (1% in 50% EtOH)	5 - 7	-	DIN EN 1262

### General product description

Property	Value	Unit	Test method
Specific gravity at 20 °C	approx 0.95	g/ml	DIN 51757
Viscosity at 25 °C	approx 90	mPas	ISO 2555
Pour point	< 5	°C	DIN ISO 3841
Refractive index n <sub>20</sub> /D	approx 1.450	-	DIN 51423

### Transport and packaging

about 850 kg containers

### Sasol Germany GmbH

Anckelmannsplatz 1, 20537 Hamburg Postanschrift: Postfach 26 18 05, 20508 Hamburg  
 Telefon: +49 40 63 684-1000 Telefax: +49 40 63 684-3700 [info@de.sasol.com](mailto:info@de.sasol.com) [www.sasol.com](http://www.sasol.com)  
 Geschäftsführung: Dr. Jens Straatmann, Judith Hübner Vorsitzender des Aufsichtsrats: Christian Schindler  
 Sitz der Gesellschaft: Hamburg Registergericht: Amtsgericht Hamburg HRB 78475



## Product Information

06.09.2023

# MARLOSOL ST 9150 P

### Storage

Stainless steel vessels (Steel No.: 1.4541 or 1.4571)

---

Data on material safety, as well as transport classes and data on toxicology and biodegradability, can be obtained from the material safety data sheet..

*This information is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party patent rights. In particular, no guarantee of properties in the legal sense is implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Reference to trade names used by other companies is neither a recommendation, nor is it intended to suggest that similar products could not be used. All our business transactions shall exclusively be governed by our General Sales Conditions.*

### Sasol Germany GmbH

Anckelmannsplatz 1, 20537 Hamburg    Postanschrift: Postfach 26 18 05, 20508 Hamburg  
Telefon: +49 40 63 684-1000    Telefax: +49 40 63 684-3700    info@de.sasol.com    www.sasol.com  
Geschäftsführung: Dr. Jens Straatmann, Judith Hübner    Vorsitzender des Aufsichtsrats: Christian Schindler  
Sitz der Gesellschaft: Hamburg    Registergericht: Amtsgericht Hamburg HRB 78475