

MARLOWET M 46 VG

Technical Data Sheet No. 5251 – March 2021



Distribuito da:




Tellerini s.p.a.

Via Bonazzi, 36
40013 Castel Maggiore (BO)
Tel: +39 051 6322111
Fax: +39 051 715380
sicurezza@tellerini.it
www.tellerini.it

Product Description

MARLOWET M 46 VG is a fatty alcohol poly-glycol ether, based on LIAL 125 and propylene oxide. It is manufactured in Terranova dei Passerini (LO) plant.

The chemical structure is the following:



R = C_nH_{2n+1} n: 11÷14 (linear and mono-branched carbon chain)

Sales Specification

Property	Test Method	Unit	Guaranteed Value ¹
√ Appearance at 25°C	ASTM D4176	-	Clear liquid
√ Colour	EN 1557	APHA	< 100
√ Hydroxyl number	EN 13926	mg KOH/g	53,0 - 58,0
√ Free Water (Karl Fischer)	ASTM E203	% mass	0,5 max
√ Kinematic viscosity (40°C)	ASTM D7042	mm ² /s	42,0 – 50,0

√ value reported on inspection certificate.

¹ specification No. D002629 rev. 2 of June 14th 2019.

Additional Properties

Property	Test Method	Unit	Typical Value
Average Molecular weight	Calculated	g/mol	1080
Pour point	ASTM D 97	°C	-54
Viscosity at 25°C	ASTM D445 / ASTM D7042	mm ² /s	124
Viscosity at 40°C	ASTM D445 / ASTM D7042	mm ² /s	48
Viscosity at 100°C	ASTM D445 / ASTM D7042	mm ² /s	9
Viscosity Index	ASTM 2270-04	-	180
Density at 25°C	ASTM D7042 / ASTM D4052	g/cm ³	0,9636
Density at 40°C	ASTM D7042 / ASTM D4052	g/cm ³	0,9488
Flash point	ASTM D 93	°C	

**sasol**

MARLOWET M 46 VG

Technical Data Sheet No. 5251 – March 2021

Main Applications

MARLOWET M 46 VG is an ash free polyalkylene glycols; due to the absence of inorganic residues, the product can be used as a fuel additive exhibiting excellent deposit control.

MARLOWET M 46 VG is a high performance Group V synthetic fluid.

MARLOWET M 46 VG may be used as a friction modifiers or coupling agent.

MARLOWET M fluids are designed for gearboxes, bearings and chains operating in the most challenging conditions; the product may also be used as a base for refrigerant lubricants.

MARLOWET M fluids provide outstanding thermal stability, excellent extreme pressure and anti-wear performance as well as protection against micro-pitting.

MARLOWET M are synthesised to give viscosities according to the ISO VG standard. Products from the MARLOWET M series may be blended together to achieve other desired viscosities.

Handling and Storage

MARLOWET M 46 VG should preferably be stored in stainless steel tanks.

It is suggested to keep the product at temperature below 30°C, it is preferable to avoid heating above 50°C and to store under nitrogen in order to minimise yellowish phenomena.

MARLOWET M 46 VG is a clear liquid at room temperature; it has pour point close to – 50°C therefore it can be easily handled even at low temperature.

Shelf-life is 36 months from production date for product in its original and sealed packaging.

Packaging

MARLOWET M 46 VG is generally supplied in bulk or in drums, details on available packaging can be obtained from sales department.

Data regarding safety, transport classes, toxicology and biodegradability of the product can be obtained from the corresponding material safety data sheet.

Sasol Italy S.p.A.

Headquarters
Viale Forlanini, 23
20134 Milano, Italy
Phone +39-02 58453 1
Fax +39-02 58453 285

Technical Customer Support
Via E. Mattei, 4
26827 Terranova dei Passerini (LO), Italy
Phone +39-0377 463 1
Fax +39-0377 463 226

Sasol is a registered trademark of Sasol Ltd. Product trademarks displayed in this document are the property of the Sasol Group of companies, except where it is clear from the context that not. Users of this document are not permitted to use these trademarks without the prior written consent of their proprietor. All rights not expressly granted are reserved. Reference to trademarks used by other companies is neither a recommendation, nor should it give the impression that products of other companies cannot be used.

The information contained in this document is based on Sasol's knowledge and experience at the time of its creation. We reserve the right to make any changes to this document or the products described therein, as a result of technological progress or developments. This information implies no liability or other legal responsibility on our part, including with regard to existing third-party patent rights. In particular, no guarantee or warranty of properties in the legal sense is implied. The customer is not exempted from the obligation to conduct careful inspection and testing of incoming products. All our business transactions are governed exclusively by our General Business Terms.