


**SASOL**

# TRIDAC ISO-6

Technical Data Sheet No. 1653 – November 2015

## Product Description

TRIDAC ISO-6 is a fatty alcohol polyethyleneglycol ether, based on MARLIPAL 13 and ethylene oxide (about 6 moles). It is manufactured in Terranova dei Passerini (LO) plant. The chemical structure is the following:



CAS registry no. 69011-36-5  
EINECS no. 931-138-8  
INCI TRIDECETH-6

## Sales Specification

Property	Test Method	Unit	Guaranteed Value <sup>1</sup>
√ Appearance at 25°C	Visual	-	Cloudy liquid
√ Colour	MPL 1002.0	APHA	≤ 50
Physical state change ment	MPL 1001.0	°C	10 – 20
√ Cloud point (10% in BDG at 25%)	MPL 2001.0	°C	72 – 74
Hydroxyl number	MPL 1010.0	mg KOH / g	110 – 120
Molecular weight	Calculated	g/mol	467 – 510
Polyethylene glycols	MPL 2002.0	% mass	≤ 3,0
√ pH (5%)	MPL 1007.0	-	5,0 – 7,0
√ Free Water (Karl Fischer)	MPL 1006.0	% mass	≤ 0,50

√ value reported on inspection certificate.

<sup>1</sup> specification No. 1940 rev. 1 of June 1<sup>st</sup> 2001.

## Additional Properties

Property	Test Method	Unit	Typical Value
Ethylene Oxide content	Calculated	%w/w	60
HLB	Calculated	-	12,1
Viscosity at 50°C	ASTM D445 / ASTM D7042	cSt	22
Density at 50°C	ASTM D7042 / ASTM D4052	kg/m <sup>3</sup>	960
Flash point	ASTM D 93	°C	> 125

RCM and MPL are Sasol Italy analytical methods, internal or referred to international standard. Additional information available upon request.



**SASOL**

# TRIDAC ISO-6

Technical Data Sheet No. 1653 – November 2015

---

## Main Applications

TRIDAC ISO-6 is a good wetting agent, with low foaming and degreasing performance.

In the detergency field TRIDAC ISO-6 is used in HDP formulations due to its high emulsification property at medium-low temperature

TRIDAC ISO-6 can be used as emulsifier for W/O or O/W emulsions in agrochemical and industrial applications, it shows good emulsifying ability towards the most common lubricant oils.

TRIDAC ISO-6 can be used also as degreasing agent in wool scouring process and leather treatment.

---

## Handling and Storage

TRIDAC ISO-6 should preferably be stored in stainless steel tanks.

It is suggested to keep the product at temperature below 40°C, it is preferable to avoid heating above 60°C and to store under nitrogen in order to minimise yellowish phenomena.

TRIDAC ISO-6 is a cloudy liquid at room temperature and it becomes a solid wax at temperature lower than 20°C. Improvement of appearance and handling at low temperature can be achieved by mixing the product with 15 weight% water to obtain a clear liquid up to a temperature about 5 C°.

At room temperature TRIDAC ISO-6 is not water soluble.

Shelf-life is 36 months from production date for product in its original and sealed packaging.

---

## Packaging

TRIDAC ISO-6 is generally supplied in drums, details on available packaging can be obtained from sales department.

---

Data regarding safety, transport classes, toxicology and biodegradability of the product can be obtained from the corresponding material safety data sheet.

---

### Sasol Italy S.p.A.

Headquarters  
Viale Forlanini, 23  
20134 Milano, Italy  
Phone +39-02 58453 1  
Fax +39-02 58453 285

Technical Customer Support  
Via E. Mattei, 4  
26827 Terranova dei Passerini (LO), Italy  
Phone +39-0377 463 1  
Fax +39-0377 463 226

This information is based on our present knowledge and experience. but it is not a guarantee of the performance of our products since the conditions of use are not under our direct control.

However, it implies no liability or other legal responsibility on our part, including any existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. All our business transactions shall be governed exclusively by our General Sales Conditions.

Sasol is a registered trademark of Sasol Ltd. Product trademarks displayed in this document are the property of the Sasol Group of Companies. Users of this document are not permitted to use these trademarks without the prior written consent of their proprietor. All rights not expressly granted are reserved.